# © Höganäs AB (publ.), December 2020. 2168H0G



# DM D2

DM D2 is an alloy based on D2 tool steel, qualified for metal AM in Digital Metal's binder jetting system.

D2 tool steel exhibits high resistance to abrasive wear and good hardenability with decent toughness, making it suitable for a wide range of applications. It is most commonly used for cutting and deformation tools, such as shear cutters, punches, dies and stamping tools.

The material is stable during heat treatments, which allows for tailoring of the final properties through various heat treatments after sintering.

## COMPOSITION - TYPICAL VALUES

C	îr	Мо	V	Mn	Si	С	Fe
12	2.0	1.0	0.9	0.5	0.3	1.5	Bal


Related standards: UNS T30402, ASTM A681, 1.2379 and SKD11

### PHYSICAL PROPERTIES - TYPICAL VALUES


Density	Hardness HRC				
Relative	As sintered	Hardened	Hardened + Tempered		
98%	35	62	58		

Hardening consists of a solution treatment with subsequent air quenching. Single tempering provides the results displayed.

# METALLOGRAPHIC STRUCTURE








As sintered Hardened

Hardened + Tempered




Specimens with subsequent process steps, bottom to top: as sintered, after hardening, after tempering and after blasting.



### **FEATURES**

- Tool steel alloy
- Provides an effective combination of abrasive wear resistance and toughness
- Suitable for a wide range of applications
- Most commonly used for cutting and deformation tools



DIGITALMETAL.TECH